

# THE EFFECT OF WASTE COOKING OIL IN WARM MIX ASPHALT

NURUL IZZATUL ALIA BINTI NAZRI

View metadata, citation and similar papers at [cobc.ac.uk](https://www.cobc.ac.uk)  
provided by UTM Institutional Repository  
Copyright © you are not to publish  **COBE**  
**B. ENG (HONS.) CIVIL ENGINEERING**

UNIVERSITI MALAYSIA PAHANG



## **SUPERVISOR'S DECLARATION**

I/We\* hereby declare that I/We\* have checked this thesis/project\* and in my/our\* opinion, this thesis/project\* is adequate in terms of scope and quality for the award of the Bachelor Degree of Civil Engineering

---

(Supervisor's Signature)

Full Name :

Position :

Date :

---

(Co-supervisor's Signature)

Full Name :

Position :

Date :



## **STUDENT'S DECLARATION**

I hereby declare that the work in this thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Malaysia Pahang or any other institutions.

---

(Student's Signature)

Full Name : NURUL IZZATUL ALIA BINTI NAZRI

ID Number : AA15186

Date : 31 MAY 2019

# THE EFFECT OF WASTE COOKING OIL IN WARM MIX ASPHALT

NURUL IZZATUL ALIA BINTI NAZRI

Thesis submitted in partial fulfillment of the requirements  
for the award of the  
B. Eng (Hons).Civil Engineering

Faculty of Civil Engineering & Earth Resources  
UNIVERSITI MALAYSIA PAHANG

MAY 2019

## **ACKNOWLEDGEMENTS**

Foremost, I want to offer this endeavor to ALLAH S.W.T for the He bestowed upon me, the strength, calmness and good health in order to complete this research.

I would like to express my gratitude to my supervisor, Assoc. Prof. Dr. Ramadhansyah Putra Jaya who always supervise me to do this research and writing until complete. Thank you for your guidance and constant supervision as well as providing necessary information for my research.

Special thanks to Mr. Sani Noh, Mrs. Siti Sarah and Mr Amir for the excellent technical assistance and kindly help me in the lab to get the best results at the Highway and Traffic Laboratory. Thanks to my lab partner Siti Noor Farzana and friends, Nurul Syazni and Nur Athirah for helping me and supporting me through the lab works.

I warmly thank my beloved parents for always supporting me and believing me during my education in this university. Thank you my mother and father for having my back throughout my life. I also would like to thank my brothers and sisters in proving assistance in numerous ways.

Thank you.

## ABSTRAK

Terdapat banyak kajian telah dilakukan untuk menentukan bahan buangan yang boleh digunakan untuk meningkatkan rintangan terhadap aluran, ubah bentuk kekal dan keletihan retak kerana pengikat pengerasan dan meningkatkan lekatan pengikat kepada agregat. Dalam kajian ini, prestasi sisa minyak memasak sebagai pengubahsuaian bitumen dalam turapan asfalt konkrit telah dikaji. Kajian ini memberi tumpuan kepada penambahan sisa minyak memasak dalam mengikuti perintah 0% sebagai kawalan, 3%, 4%, dan 5% oleh berat bitumen. Tujuan kajian ini adalah untuk mengkaji kesan sisa minyak memasak pada ciri-ciri kejuruteraan Asfalt Konkrit 14. peratusan yang berbeza sisa minyak memasak telah dicampur ke dalam bitumen dengan menggunakan pengadun ricih yang tinggi pada kelajuan malar 1000 rpm selama satu jam pada 140 °C. ujian Marshall Kestabilan telah dijalankan untuk menentukan kandungan bitumen optimum campuran. Prestasi sampel dinilai melalui kestabilan dan isipadu sifat-sifat, modulus kebingkasan dan rayapan dinamik.

## ABSTRACT

There are many studies have been done to determine the waste material that can be used to improve resistance to rutting, permanent deformation and fatigue cracking due to binder hardening and improve adhesion of binder to aggregate. In this study, the performance of Waste Cooking Oil (WCO) as a bitumen modifier in asphalt concrete pavement was investigated. This study focuses on the addition of WCO in following order 0% as control, 3%, 4%, and 5% by the weight of bitumen. The aim of this study is to investigate the effect of WCO on the engineering properties of Asphaltic Concrete 14. The different percentage of WCO was blended into the bitumen using a high shear mixer at a constant speed of 1000 rpm for one hour at 140°C. Marshall Stability test was carried out to determine the optimum bitumen content of the mixture. The performance of the samples was evaluated through the stability and volumetric properties, resilient modulus and dynamic creep.

## **TABLE OF CONTENT**

### **DECLARATION**

### **TITLE PAGE**

ACKNOWLEDGEMENTS	ii
------------------	----

ABSTRAK	iii
---------	-----

ABSTRACT	iv
----------	----

TABLE OF CONTENT	v
------------------	---

LIST OF TABLES	ix
----------------	----

LIST OF FIGURES	x
-----------------	---

LIST OF ABBREVIATIONS	xi
-----------------------	----

CHAPTER 1 INTRODUCTION	<b>1</b>
------------------------	----------

1.1 Introduction	1
------------------	---

1.2 Problem Statement	3
-----------------------	---

1.3 Objectives	4
----------------	---

1.4 Scope of Research	4
-----------------------	---

1.5 Significance of Research	5
------------------------------	---

<b>CHAPTER 2 LITERATURE REVIEW</b>	<b>6</b>
------------------------------------	----------

2.1 Introduction	6
------------------	---

2.2 Warm Mix Asphalt	7
----------------------	---

2.3 Bitumen	7
-------------	---

2.4 Waste Material in Warm Mix Asphalt	7
--	---

2.5 Waste Cooking Oil	8
-----------------------	---



<b>CHAPTER 3 METHODOLOGY</b>	<b>10</b>
3.1 Introduction	10
3.2 Flow Chart of Study	11
3.3 Waste Cooking Oil	12
3.3.1 Acid Value Test	12
3.3.1 Transesterification	13
3.4 Bitumen Content	15
3.4.1 Preparation of Materials	16
3.4.2 Penetration Test	17
3.4.3 Softening Point Test	18
3.5 Aggregate	20
3.5.1 Aggregate Gradation	20
3.6 Marshall Mix design	22
3.7 Marshall Mix Design Analysis	25
3.7.1 Bulk Density Gravity	26
3.7.2 Stability and Flow	28
3.7.3 Stiffness	30
3.7.4 Voids Filled with Bitumen	30
3.7.5 Voids in Total Mix	30
3.7.6 Volume in Mineral Aggregate	30
3.8 Resilient Modulus	31
3.9 Dynamic Creep	34

<b>CHAPTER 4 RESULTS AND DISCUSSION</b>	<b>37</b>
4.1 Introduction	37
4.2 Aggregate Gradation	38
4.3 Penetration	39
4.4 Softening Point	40
4.5 Acid Value	41
4.6 Marshall Stability and Flow	42
4.6.1 Determination of Marshall Properties	42
4.7 Marshall Stability Properties	43
4.7.1 Density	43
4.7.2 Stability	44
4.7.3 Flow	45
4.7.4 Stiffness	46
4.7.5 Voids Filled with Bitumen	47
4.7.6 Voids in Total Mix	48
4.7.7 Volumes in Mineral Aggregate	49
4.8 Stability, Flow and WCO Content	50
4.9 Stability, Density and WCO Content	52
4.10 Stiffness, Density and WCO Content	53
4.121 Resilient Modulus	53
4.12 Dynamic Creep	55
<b>CHAPTER 5 CONCLUSION</b>	<b>56</b>
5.1 Introduction	56
5.2 Conclusion	56
5.3 Recommendations	58



## **LIST OF TABLES**

Table 3.1	Gradation Limit for AC14	21
Table 3.2	Amount of WCO and Bitumen in Mix for Marshall	23
Table 3.3	Sample Preparation for Marshall	24
Table 3.4	Amount of WCO and Bitumen in Mix for Resilient Modulus	31
Table 3.5	Sample Preparation for Resilient Modulus	32
Table 3.6	Amount of WCO and Bitumen in Mix for Dynamic Creep	34
Table 3.7	Sample for Creep Modulus	35
Table 4.1	Sieve Analysis result	38
Table 4.2	Acid Value result	41
Table 4.3	Marshall Stability and Flow results	42

## LIST OF FIGURES

Figure 3.1	Flow Chart of Study	11
Figure 3.2	Automatic Acid Value Machine	13
Figure 3.3	Reactor Tank for Transesterification	14
Figure 3.4	High Shear Mixture	16
Figure 3.5	Automatic Penetration Machine	18
Figure 3.6	Softening Point Test	19
Figure 3.7	Sieve Shaker Machine	22
Figure 3.8	Compactor Machine	25
Figure 3.9	Sample Submerged in Water	27
Figure 3.10	Samples Immersed in Water Bath at 60°C	28
Figure 3.11	Machine for Stability and Flow Test	29
Figure 3.12	Resilient Modulus Test	33
Figure 3.13	Dynamic Creep Test	36
Figure 4.1	Penetration at 25°C	39
Figure 4.2	Softening Point	40
Figure 4.3	Density against WCO Content	43
Figure 4.4	Stability against WCO Content	44
Figure 4.5	Flow against WCO Content	45
Figure 4.6	Stiffness against WCO Content	46
Figure 4.7	Voids Filled with Bitumen against WCO Content	47
Figure 4.8	Voids in Total Mix against WCO Content	48
Figure 4.9	Volume in Mineral aggregate against WCO Content	49
Figure 4.10	Stability and Flow at Different WCO Content	50
Figure 4.11	Stability and Density at Different WCO Content	51
Figure 4.12	Stiffness and Density at Different WCO Content	52
Figure 4.13	Resilient Modulus at 25°C	54
Figure 4.14	Resilient Modulus at 40°C	54
Figure 4.15	Dynamic Creep at 40°C	55

## **LIST OF ABBREVIATIONS**

WMA	Warm mix asphalt
HMA	Hot mix asphalt
AC 14	Asphalt concrete 14
WCO	Waste cooking oil
JKR	Jabatan Kerja Raya
ASTM	American Society for Testing and Materials
BS EN	British Standard European
VFB	Voids Filled with bitumen
VTM	Voids in Total Mix
VMA	Voids in Mineral Aggregate
UTM	Universal Testing Machine
KOH	Potassium Hydroxide
NaOH	Sodium Hydroxide

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Introduction**

Most roads in Malaysia are applying the Hot Mix Asphalt (HMA) or asphalt concrete on the roadway because HMA pavement classified as flexible pavement due to the total pavement structure that deflects under loading. The asphaltic concrete pavement mixture is conventionally composed of 5% asphalt cement and 95% aggregates such as stones, sand and gravel. Asphalt concrete locks the soil surface which regulates the rainwater from percolation & natural recharge from the ground (Bhavana, 2017). Asphalt concrete must be heated to be mix with aggregates due to highly viscous properties. Asphalt is a dark brown to black is a highly viscous, hydrocarbon produced from the petroleum distillation residue. Lately, the asphalt industry has been concerned about the sustainable roadway to reduce the pollution and environmental friendly on global warming as the HMA pavement may emit the gas that is harmful to the environment and the heating of asphalt at high temperature causes the binder to lose its viscosity.

As petroleum asphalt becomes in short supply as a non-renewable resource, a lot of noteworthy studies conducted all around the world to investigate possible resource from waste materials as additive or replacement of asphalt and binder (Wan Azahar et al, 2016). Hence, waste cooking oil is one of the significant studies that highlighted the best performance and workability of waste materials as asphalt binder substitute. Not only that, waste cooking oil can diminish the environmental issues such as wastewater treatment and waste oil disposal due to the littering activity of the waste cooking oil into the landfill or river by recycling it or treat the waste cooking oil. Additive or replacement materials that are used in bitumen are designed to against fatigue, rutting, thermal cracking, and moisture susceptibility, therefore the laboratory performance conducted to evaluate the properties of the waste cooking oil. Due to the degradation process from the

frying activity, the quality of waste cooking oil was affect the modified asphalt binder later. In order to overcome this issue, a chemical test was be done to treat and get a better quality of waste cooking oil

Warm Mix Asphalt (WMA) is a kind of new pavement material, which the temperature used during mixing activities is 100°C to 140°C and it is between hot mix asphalt and cold mix asphalt, and the performance of this pavement material is close to Hot Mix Asphalt (HMA). In general terms, Warm Mix Asphalt technology gives benefits for better construction environment and higher recyclability of materials that related to the reduction of fuel consumption and gases emission by lowering the temperature during mixing compared to Hot Mix Asphalt (HMA), (Shuang Wu & Shunzhi Qian, 2014). It is because when using the traditional Hot Mix Asphalt (HMA), the construction pavement of asphalt concrete not only consumes enormous amounts of energy, but HMA also emits the greenhouse gases that harmful to the environment and lead to the air pollution. By using the new pavement method of Warm Mix Asphalt it was ensure the good workability and sensible long term performance of the asphalt.



## **1.2 Problem Statement**

Road infrastructures play an important role in the growing economy industry and a great investment. Public roads play a critical role in aspect and reflecting the country's developing status. Having a sustainable road infrastructure design requires a good balance between environment, cost and social aspects (Saad Issa, 2015). Sustainability in road infrastructure should be addressed with the understanding that highway is one part of transportation infrastructure that meets the human needs. Transportation makes the movement on roadways from one place to another place between the cities and towns. The travelling of the transports including cars, buses and lorries, lead to negative externalities in the form of overcrowding and traffic jam conditions on the roads, accidents, greenhouse emissions and air pollution and psychological and another health hazards (Chidambara,2010).

Cooking oil as an additive and medium of heat transfer plays a remarkable role in food preparation. It is one of the elements that provide the food with good taste, colour and aroma favoured by consumers. Recently, a big volume of waste cooking oil (WCO) is produced and released into the environment in various countries of the world. Waste Cooking Oil which is expected to be treated and handled in a good way that could not be harmful to the human health and to the environment, is being disposed of by consumers via sink, waste bins, drainage systems, toilets or directly to the immediate water bodies and lands.

Warm Mix Asphalt represents the technologies that allow reducing of asphalt binder mixing and compaction temperature by reducing its binder viscosity. Global energy insufficiency and weather conditions have become serious issues commonly concerned by the international community, and it has been the common responsibility of each country to save energy, reduce emissions and ensure sustainable development. By implying the Warm Mix Asphalt techniques, is not only concerned towards environmental issues but it also beneficial towards the economic, construction and recycling issues. By lowering the temperature during mixing and compaction of asphalt, it does not disturb the properties of the mixture instead it provides more work friendly

## REFERENCES

- Azahar, W. N. A. W. *et al.* (2016) 'Chemical modification of waste cooking oil to improve the physical and rheological properties of asphalt binder', *Construction and Building Materials*. Elsevier, 126, pp. 218–226. doi: 10.1016/J.CONBUILDMAT.2016.09.032.
- Hidayah, N. *et al.* (2014) 'Warm Mix Asphalt Technology : A Review Jurnal Teknologi Warm Mix Asphalt Technology : A Review', 3(December), pp. 39–52. doi: 10.11113/jt.v71.3757.
- El-gendy, N. S. *et al.* (2015) 'Response Surface Optimization of an Alkaline Transesterification of Waste Cooking Oil', 8(8), pp. 385–398.
- Jabatan Kerja Raya (2008). Standard Specification for Road Works JKR/SPJ/2008-S4. *Kuala Lumpur*.
- 'Laboratory Evaluation of Warm Mix Asphalt Mixtures in South Dakota, USA' (2011), (August).
- J-Oldham. The Feasibility of Rejuvenating Aged Asphalt with Bio-Oil from Swine Manure. North Carolina A&T State University. (2015)
- Abdallah Sayed Ahmed Ali El-Gharbawy (2016) 'Production of Biodiesel from Non Edible Vegetable Oil', pp. 1–91.
- Abdullah, M. E. *et al.* (2014) 'Jurnal Teknologi Warm Mix Asphalt Technology : A Review', 3, pp. 39–52.
- Al-saeedi, B. J. K. (2018) 'Sustainable Performance of Iraqi Asphalt Base Course Using Recycled Glass as Aggregate Replacement', (5), pp. 63–80.
- Azahar, W. N. A. W. *et al.* (2016) 'The potential of waste cooking oil as bio-asphalt for alternative binder – An overview', *Jurnal Teknologi*, 78(4), pp. 111–116. doi: 10.11113/jt.v78.8007.
- Banani, R. *et al.* (2015) 'Waste Frying Oil with High Levels of Free Fatty Acids as one of the prominent sources of Biodiesel Production', 6(4), pp. 1178–1185.

- Bhavana, T. D. (2017) 'PERVIOUS CONCRETE PAVEMENT', 8(4), pp. 413–421.
- Dinis-Almeida, M. *et al.* (2016) 'Performance of Warm Mix Recycled Asphalt containing up to 100% RAP', *Construction and Building Materials*. Elsevier Ltd, 112, pp. 1–6. doi: 10.1016/j.conbuildmat.2016.02.108.
- Guerrero F., C. A., Guerrero-Romero, A. and E., F. (2011) 'Biodiesel Production from Waste Cooking Oil', *Biodiesel - Feedstocks and Processing Technologies*. doi: 10.5772/25313.
- Guerrero F., C. A., Guerrero-Romero, A. and E., F. (2011) 'Biodiesel Production from Waste Cooking Oil', *Biodiesel - Feedstocks and Processing Technologies*. doi: 10.5772/25313.
- Hashi, N. A., Rahman, K. M. and Begum, M. (2016) 'Assessment the Performance of Roadway : A Study on Muradpur to Dewanhat Road, Chittagong, Bangladesh', (February), pp. 5–6.
- Janajreh, I. *et al.* (2015) 'Transesterification of Waste Cooking Oil : Kinetic Study and Reactive Flow Analysis', *Energy Procedia*. Elsevier B.V., 75, pp. 547–553. doi: 10.1016/j.egypro.2015.07.451.
- Jiaotong, X. and Xuebao, D. (2018) 'EFFECT OF NANO BLACK RICE HUSK ASH ON THE CHEMICAL AND PHYSICAL', (November).
- Kabir, I., Yacob, M. and Radam, A. (2014) 'Households' Awareness, Attitudes and Practices Regarding Waste Cooking Oil Recycling in Petaling, Malaysia', *IOSR Journal of Environmental Science Ver. III*, 8(10), pp. 2319–2399. doi: 10.9790/2402-081034551.
- Khan, K. M. and Kamal, M. A. (2012) 'Rutting Based Evaluation of Asphalt Mixes', 11(2006), pp. 60–65.
- Kho, F. W. L. *et al.* (2007) 'Carbon monoxide levels along roadway', *International Journal of Environmental Science and Technology*, 4(1), pp. 27–34. doi: 10.1007/BF03325958.

- Kumar, R. and Chandra, S. (2016) 'Warm Mix Asphalt Investigation on Public Roads - A Review', *Civil Engineering and Urban Planning: An International Journal (CiVEJ)*, 3(2), pp. 75–86. doi: 10.5121/civej.2016.3206.
- Kumar, R. and Chandra, S. (2016) 'W ARM M IX A SPHALT I NVESTIGATION O N P UBLIC R OADS -A R EVIEW', 3(2), pp. 75–86. doi: 10.5121/civej.2016.3206.
- Method, H. (2012) 'MARSHALL MIX DESIGN AND ANALYSIS', pp. 48–77.
- Nur, W. *et al.* (2016) 'Jurnal Teknologi BIO-ASPHALT FOR ALTERNATIVE BINDER – AN', (March). doi: 10.11113/jt.v78.8007.
- Patel, A. *et al.* (2011) 'A Methodology for Determination of Resilient Modulus of Asphaltic Concrete', 2011. doi: 10.1155/2011/936395.
- Rahman, M. T., Hainin, M. R. and Bakar, W. A. W. A. (2017) 'Use of waste cooking oil, tire rubber powder and palm oil fuel ash in partial replacement of bitumen', *Construction and Building Materials*. Elsevier Ltd, 150, pp. 95–104. doi: 10.1016/j.conbuildmat.2017.05.216.
- Rahman, T. *et al.* (2017) 'Use of waste cooking oil, tire rubber powder and palm oil fuel ash in partial replacement of bitumen', *Construction and Building Materials*. Elsevier Ltd, 150, pp. 95–104. doi: 10.1016/j.conbuildmat.2017.05.216.
- Report, F. (2012) 'Accelerated Testing of Warm Asphalt Mixtures for Safe and Reliable Freight Transportation Written by', (July).
- Romastarika, R. and Putra, R. (2017) 'The Effect of Black Rice Husk Ash on the Rheological Properties of Bitumen', (c), pp. 305–314.
- Sarsam, S. I. (2015) 'Mini Review Paper Sustainable and Green Roadway Rating System', 3(3), pp. 99–106.
- Vlachos, D. G. and Hale, K. J. (no date) 'Chemical Engineering & Process Technology Biodiesel from Household / Restaurant Waste Cooking Oil (WCO)'. doi: 10.4172/2157-7048.1000112.

- Wen, H., Bhusal, S. and Wen, B. (2013) 'Laboratory Evaluation of Waste Cooking Oil-Based Bioasphalt as an Alternative Binder for Hot Mix Asphalt', *Journal of Materials in Civil Engineering*, 25(10), pp. 1432–1437. doi: 10.1061/(ASCE)MT.1943-5533.0000713.
- Wu, S. and Qian, S. (2015) 'COMPARISON OF WARM MIX ASPHALT AND HOT MIX ASPHALT PAVEMENT BASED ON LIFE CYCLE ASSESSMENT', pp. 87–96.
- Wulandari, P. S. and Tjandra, D. (2017) 'Use of Crumb Rubber as an Additive in Asphalt Concrete Mixture', *Procedia Engineering*, 171, pp. 1384–1389. doi: 10.1016/j.proeng.2017.01.451.
- Zargar, M. *et al.* (2012) 'Investigation of the possibility of using waste cooking oil as a rejuvenating agent for aged bitumen', pp. 1–2.
- Zumrawi, M. M. E. and Sheikh Edrees, S. A. (2016) 'Comparison of Marshall and Superpave Asphalt Design Methods for Sudan Pavement Mixes', *International Journal of Scientific and Technical Advancements*, 2(1), pp. 29–35.